

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>H01J 9/02, 1/30</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/31702</b> <b>(43) International Publication Date:</b> 24 June 1999 (24.06.99)
<b>(21) International Application Number:</b> PCT/US98/26018 <b>(22) International Filing Date:</b> 8 December 1998 (08.12.98)  <b>(30) Priority Data:</b> 60/069,457 15 December 1997 (15.12.97) US  <b>(71) Applicant (for all designated States except US):</b> E.I. DU PONT DE NEMOURS AND COMPAGNY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> AMEY, Daniel, Irwin, Jr. [US/US]; 6 Middlesborough Court, Durham, NC 27705 (US). BOUCHARD, Robert, Joseph [US/US]; 20 Crestfield Road, Wilmington, DE 19810 (US). SHAH, Syed, Ismat, Ullah [PK/US]; 2808 Bexley Court, Wilmington, DE 19808 (US).  <b>(74) Agent:</b> SCHAEFFER, Andrew, L.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> CN, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> ION BOMBARDED GRAPHITE ELECTRON EMITTERS  <b>(57) Abstract</b>  Patterned graphite electron emitters are disclosed. These field emitters find particular usefulness in field emitter cathodes and display panels. These graphite field emitters can be formed by screen printing a paste comprised of graphite and electrically insulating material (glass frit) in the desired patterned paste and bombarding the fire product with an ion beam.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLE

ION BOMBARDED GRAPHITE ELECTRON EMITTERS

FIELD OF THE INVENTION

This invention provides patterned ion bombarded graphite field emission  
5 electron emitters, a process for producing them and their use in field emitter  
cathodes in flat panel display screens.

BACKGROUND OF THE INVENTION

Field emission electron sources, often referred to as field emission  
materials or field emitters, can be used in a variety of electronic applications, e.g.,  
10 vacuum electronic devices, flat panel computer and television displays, emission  
gate amplifiers and klystrons and in lighting.

Display screens are used in a wide variety of applications such as home  
and commercial televisions, laptop and desktop computers and indoor and outdoor  
advertising and information presentations. Flat panel displays are only a few  
15 inches thick in contrast to the deep cathode ray tube monitors found on most  
televisions and desktop computers. Flat panel displays are a necessity for laptop  
computers, but also provide advantages in weight and size for many of the other  
applications. Currently laptop computer flat panel displays use liquid crystals  
which can be switched from a transparent state to an opaque one by the  
20 application of small electrical signals. It is difficult to reliably produce these  
displays in sizes larger than that suitable for laptop computers or for operation  
over a wide temperature range.

Plasma displays have been used as an alternative to liquid crystal displays.  
A plasma display uses tiny pixel cells of electrically charged gases to produce an  
25 image and requires relatively high electrical power to operate.

Flat panel displays having a cathode using a field emission electron source,  
i.e., a field emission material or field emitter, and a phosphor capable of emitting  
light upon bombardment by electrons emitted by the field emitter have been  
proposed. Such displays have the potential for providing the visual display  
30 advantages of the conventional cathode ray tube and the depth and weight  
advantages of the other flat panel displays with the additional advantage of lower  
power consumption than the other flat panel displays.

U.S. Patents 4,857,799 and 5,015,912 disclose matrix-addressed flat panel  
displays using micro-tip cathodes constructed of tungsten, molybdenum or silicon.  
35 WO 94-15352, WO 94-15350 and WO 94-28571 disclose flat panel displays  
wherein the cathodes have relatively flat emission surfaces.

Field emission has been observed in two kinds of nanotube carbon  
structures. L. A. Chernozatonskii et al., Chem. Phys. Letters 233, 63 (1995) and  
Mat. Res. Soc. Symp. Proc. Vol. 359, 99 (1995) have produced films of nanotube

carbon structures on various substrates by the electron evaporation of graphite in  $10^{-5}$  -  $10^{-6}$  torr. These films consist of aligned tube-like carbon molecules standing next to one another. Two types of tube-like molecules are formed; the A-tubelites whose structure includes single-layer graphite-like tubules forming  
5 filaments-bundles 10-30 nm in diameter and the B-tubelites, including mostly multilayer graphite-like tubes 10-30 nm in diameter with conoid or dome-like caps. They report considerable field electron emission from the surface of these structures and attribute it to the high concentration of the field at the nanodimensional tips. B. H. Fishbine et al., Mat. Res. Soc. Symp. Proc. Vol. 359,  
10 93 (1995) discuss experiments and theory directed towards the development of a buckytube (i.e., a carbon nanotube) cold field emitter array cathode.

R. S. Robinson et al., J. Vac. Sci. Technolo. 21, 1398 (1983) disclose the formation of cones on the surfaces of substrates under ion bombardment. The effect was reported for various substrate materials and were generated by  
15 simultaneously sputtering a surface at high energy while seeding it with impurity atoms deposited at low energy. They also disclosed the formation of carbon whiskers up to 50  $\mu\text{m}$  in length when a graphite substrate was ion-bombarded with impurities from a stainless steel target.

J. A. Floro et al., J. Vac. Sci. Technolo. A 1, 1398 (1983) disclose the  
20 formation of whiskers during relatively high current density ion bombardment of heated graphite substrates. The whiskers were disclosed to be 2-50  $\mu\text{m}$  in length and 0.05-0.5  $\mu\text{m}$  in diameter and to grow parallel to the ion beam. Simultaneous impurity seeding was reported to inhibit whisker growth. J. A. van Vechten et al., J. Crystal Growth 82, 289 (1987) discuss the growth of whiskers from graphite  
25 surfaces under ion sputtering conditions. They note that the whiskers of smallest diameter, characteristically about 15 nm, definitely appear to be different from either diamond or the scrolled-graphite structure found in carbon fibers grown by catalytic pyrolysis of hydrocarbons. Larger whiskers with diameters ranging from 30 to 100 nm were also observed to grow in sputtering systems. The smaller  
30 diameter whiskers are constant in diameter along the length while the larger diameter whiskers may have a slight taper.

M. S. Dresselhaus et al., Graphite Fibers and Filaments (Springer-Verlag, Berlin, 1988), pp. 32-34, disclose that filaments may be grown on several types of hexagonal carbon surfaces, but not on diamond or glassy carbon.

35 T. Asano et al., J. Vac. Sci. Technol. B 13, 431 (1995) disclose increased electron emission from diamond films which have been deposited on silicon by chemical vapor deposition, argon ion milled to form diamond cones and then annealed at 600°C. These cones are formed if the diamond is in the form of isolated grains.

C. Nützenadel et al., Appl. Phys. Lett. 69, 2662 (1996) disclose field emission from cones etched into both synthetic boron-doped diamond and silicon by ion sputtering.

5 S. Bajic et al., J. Phys. D: Appl. Phys. 21, 200 (1988) disclose a field emitter composite with graphite particles suspended in a resin layer.

R. A. Tuck et al., WO 97/06549, disclose a field emission material comprising an electrically conductive substrate and, disposed thereon, electrically conductive particles embedded in, formed in, or coated by a layer of inorganic electrically insulating material to define a first thickness of the insulating material  
10 between the particle and the substrate and a second thickness of the insulating material between the particle and the environment. The field emitting material may be printed onto a substrate.

There is a need for a process for readily and economically producing both small and large sized highly emitting field emission electron emitters for use in  
15 various flat panel applications.

#### SUMMARY OF THE INVENTION

This invention provides a process for producing a field emission electron emitter, which comprises:

- 20 (a) forming a layer of composite which comprises graphite particles embedded in a matrix material which comprises electrically insulating material, wherein the matrix material adheres to a substrate and to the graphite particles thereby affixing the graphite particles to one another and to the substrate and wherein the graphite particles are essentially completely  
25 surrounded by the matrix material, and
- (b) bombarding the surface of the layer formed in (a) with an ion beam.

Preferably the ion beam is an argon ion beam and the argon ion beam has an ion current density of from about 0.1 mA/cm<sup>2</sup> to about 1.5 mA/cm<sup>2</sup>, a beam  
30 energy of from about 0.5 keV to about 2.5 keV and a period of ion bombardment of at least about 15 minutes.

Preferably the electrically insulating material is glass and most preferably, a glass with a low softening point.

Preferably, when the layer of composite comprises graphite and glass, the  
35 process for forming the layer of composite on a substrate comprises screen printing a paste comprised of graphite particles and glass frit onto the substrate in the desired pattern and firing the patterned paste. For a wider variety of applications, e.g., those requiring finer resolution, the preferred process comprises screen printing a paste which further comprises a photoinitiator and a

photohardenable monomer, photopatterning the dried paste and firing the patterned paste.

This invention also provides a process for producing a field emission electron emitter wherein the matrix material further comprises electrically  
5 conducting material. Preferably the electrically conducting material is silver or gold.

Preferably, when the layer of composite further comprises an electrically conducting material, the process for forming the layer of composite on a substrate comprises screen printing a paste comprised of graphite, glass frit and an  
10 electrically conducting material onto the substrate in the desired pattern and firing the patterned paste. For a wider variety of applications, e.g., those requiring finer resolution, the preferred process comprises screen printing a paste which further comprises a photoinitiator and a photohardenable monomer, photopatterning the dried paste and firing the patterned paste.

15 This invention also provides a screen printable or coatable paste that can be used in the preferred process for embedding graphite particles in glass. The paste contains solids comprised of graphite particles and glass frit.

This invention also provides electron emitters produced by the process of this invention. These electron emitters and field emitter cathodes made therefrom  
20 are useful in vacuum electronic devices, flat panel computer and television displays, emission gate amplifiers, klystrons and lighting devices. The flat panel displays can be planar or curved.

#### DETAILED DESCRIPTION OF THE INVENTION

The process of the invention for producing a field emission electron  
25 emitter comprises embedding graphite particles in a matrix which comprises electrically insulating material and may further comprise electrically conducting material. The matrix material adheres to a substrate and the graphite particles are embedded within the matrix and are thereby affixed to the substrate. The graphite particles are essentially completely surrounded by matrix material.

30 As used herein, "graphite particles" means the particles of the usual hexagonal graphite as well as particles of amorphous carbon which are microcrystalline forms of graphite.

As used herein, "essentially completely surrounded by the matrix material" means that the graphite particles are embedded or encased within or coated by the  
35 matrix material. Some small portions of the some of the graphite particles may not be coated by the matrix material.

Preferably the electrically insulating material is glass and most preferably, a glass with a low softening point.

Various processes can be used to embed the graphite particles in the matrix material, but the preferred process is to screen print a paste comprised of graphite particles and matrix material, e.g., glass frit or glass frit and a good electrically conducting metal, onto a substrate. The dried paste is then photopatterned and the  
5 patterned paste fired. Alternatively, the desired pattern of paste is formed during the screen printing step and the dried paste is then fired. The patterned paste is fired to soften the glass frit and cause it to adhere to the substrate and to portions of the graphite particles thereby affixing the graphite particles to one another and to the substrate to produce the layer of composite.

10 The substrate can be any material to which the matrix material will adhere. Non-conducting substrates will require a film of an electrical conductor to serve as the cathode electrode and provide means to apply a voltage to and supply electrons to the graphite particles. Silicon, a glass, a metal or a refractory material such as alumina can serve as the substrate.

15 As used herein, "substrate" means the structure on which the layer of composite is formed, either a single material or a combination of materials, e.g., a non-conducting material such as glass with a layer of an electrical conductor. A preferred technique for providing such an electrically conducting layer is to form a conducting composite by screen printing and firing a silver or gold conductor  
20 composition.

When screen printing or photopatterning is used to form a layer of composite, the preferable substrate is glass and soda lime glass is especially preferred.

The paste used for screen printing typically contains graphite particles, low  
25 softening point glass frit, an organic medium, solvent and surfactant. The role of the medium and solvent is to suspend and disperse the particulate constituents, i.e., the solids, in the paste with a proper rheology for typical patterning processes such as screen printing. There are a large number of such mediums known in the art. Examples of resins that can be used are cellulosic resins such as ethyl  
30 cellulose and alkyd resins of various molecular weights. Butyl carbitol, butyl carbitol acetate, dibutyl carbitol, dibutyl phthalate and terpineol are examples of useful solvents. These and other solvents are formulated to obtain the desired viscosity and volatility requirements. A surfactant can be used to improve the dispersion of the particles. Organic acids such oleic and stearic acids and organic  
35 phosphates such as lecithin or Gafac® phosphates are typical surfactants. A glass frit that softens sufficiently at the firing temperature to adhere to the substrate and to the graphite particles is required. Preferably the graphite particles have least dimensions of 1  $\mu\text{m}$ . If a layer of composite with higher electrical conductivity is desired, the paste also contains a metal such as silver or gold. Since the graphite

particles are to be surrounded by glass it would be appropriate to add a wetting agent such as lead nitrate to the paste to promote the wetting of the graphite particles by the glass. Variations in the composition can be used to adjust the viscosity and the final thickness of the printed material.

5       The paste is typically prepared by milling a mixture of graphite particles, low softening point glass frit, organic medium, surfactant, a wetting agent and a solvent. The paste mixture can be screen printed using well-known screen printing techniques, e.g., by using a 165-400 mesh stainless steel screen. The paste is deposited in the form of a desired pattern, e.g., discrete elements,  
10   interconnected areas or a continuous film. The screen-printed paste is dried before firing, typically by heating at 125°C for about 10 minutes. When the substrate comprises glass, the dried paste is then fired at a temperature of about 450°C to about 575°C, preferably at about 525°C, for about 10 minutes. Higher firing  
15   temperatures can be used with substrates which can endure them. It is during this firing step that the organic materials are volatilized leaving the layer of composite comprised of graphite particles and glass. Surprisingly, the graphite particles undergo no appreciable oxidation or other chemical or physical change during the firing.

20       If the screen-printed paste is to be photopatterned, the paste contains a photoinitiator and a photohardenable monomer comprised, for example, of at least one addition polymerizable ethylenically unsaturated compound having at least one polymerizable ethylenic group.

25       The layer of deposited paste decreases in thickness upon firing. Preferably, the thickness of the fired layer of composite is from about 5  $\mu\text{m}$  to about 30  $\mu\text{m}$ .

30       The layer of composite which comprises graphite particles and glass on a substrate can be subsequently treated to produce a field emission electron emitter. For example, the layer of composite is then subjected to ion beam bombardment under the following conditions. Beams of argon, neon, krypton or xenon ions can be used. Argon ions are preferred. The pressure during this bombardment is about  $0.5 \times 10^{-4}$  torr ( $0.7 \times 10^{-2}$  Pa) to about  $5 \times 10^{-4}$  torr ( $6.7 \times 10^{-2}$  Pa). The ion beam bombardment is carried out at ion current densities of about 0.1 mA/cm<sup>2</sup> to about 1.5 mA/cm<sup>2</sup>, preferably about 0.5 mA/cm<sup>2</sup> to about 1.2 mA/cm<sup>2</sup>, with beam  
35   energies of about 0.5 keV to about 2.5 keV, preferably about 1.0 keV to about 1.5 keV. Bombardment times of about 10 minutes to 90 minutes or more can be used. Under these conditions, glass is removed from the graphite particles near the surface of the layer of composite to expose the graphite and whiskers and cones are formed on the graphite particle surfaces. The resulting product will be a good field emission electron emitter. Ranges of the exposure times and optimal



exposure times depend on the other bombardment conditions. Bombardment must be for a time sufficient to result in the removal of the glass from the graphite particles and the formation of the whiskers and cones on the graphite particles.

Any ion source can be used. Currently Kaufmann Ion Sources are the most readily available commercially.

The surface structure of the layer of composite will change significantly during the ion bombardment. Glass is removed from the surfaces of the graphite particles at the layer surface. As a result of etching, it is no longer smooth, but instead becomes textured with the formation of cones on the graphite particles.

Diameters of the cones range from about 0.1  $\mu\text{m}$  to about 0.5  $\mu\text{m}$ . The cones develop in the direction toward the incident ion beam so that when ion beam etching is carried out at angles other than 90° (e.g., normal to the surface), the cones are not normal to the surface. The graphite etches uniformly over the area bombarded, i.e., the density of the cones (the number of cones per unit area) and the appearance of the cones is uniform.

Transmission electron micrographs of the cones formed will indicate that they consist of small grains of crystalline carbon. A cone is believed to be that part of the original graphite surface which is left behind following ion beam etching.

In addition to the cones, whiskers are also formed during ion bombardment of the graphite particle surfaces. Whiskers are typically located at the tips of the cones. The lengths of the whiskers can extend from 2  $\mu\text{m}$  to distances of 20  $\mu\text{m}$  or more. The lengths of the whiskers can be much greater than the initial dimensions of the graphite particles. Diameters of the whiskers are in the range of 0.5 to 50 nm. The whiskers form in the direction toward the incident ion beam. The whiskers are flexible, and will move during scanning electron microscopy measurements.

A 3 cm-diameter ion gun (Kauffman Ion Source, Model II) can be used to create an argon ion beam of about 2 inches diameter (5 cm) at the sample surface. This is a turbo-pumped system with a base pressure of  $1 \times 10^{-8}$  torr ( $1.3 \times 10^{-6}$  Pa). After the base pressure is reached, the working gas, argon, is fed into the system through a needle valve until a steady working pressure of  $1 \times 10^{-4}$  torr ( $1.3 \times 10^{-2}$  Pa) was achieved. The distance between the ion gun and the surface is 4-5 inches (10-12.5 cm).

Transmission electron micrographs of the whiskers will indicate that they are solid and consist of amorphous carbon. This material is believed to be carbon which has been removed from the original graphite particles by ion beam etching and then redeposited, initially typically at the tips of cones and then at the tips of the growing whiskers. Alternately, the whiskers may form by carbon activated by

the ion beam which diffuses to the tips of the cones or whiskers. These carbon whiskers differ in structure from carbon nanotubes. Carbon nanotubes are hollow and contain shells of graphite-like sheets of carbon. Carbon whiskers are solid and exhibit no long range crystalline order in any direction.

5           Field emission tests can be carried out on the resulting samples using a flat-plate emission measurement unit comprised of two electrodes, one serving as the anode or collector and the other serving as the cathode. The unit is comprised of two square copper plates, 1.5 in by 1.5 in (3.8 cm x 3.8 cm), with all corners and edges rounded to minimize electrical arcing. Each copper plate is embedded  
10 in a separate polytetrafluoroethylene (PTFE) block, 2.5 in x 2.5 in (4.3 cm x 4.3 cm), with one 1.5 in by 1.5 in (3.8 cm x 3.8 cm) copper plate surface exposed on the front side of the PTFE block. Electrical contact to the copper plate is made by a metal screw through the back of the PTFE block and extending into the copper plate, thereby providing a means to apply an electrical voltage to the plate  
15 and means to hold the copper plate firmly in place. The two PTFE blocks are positioned with the two exposed copper plate surfaces facing one another and in register with the distance between the plates fixed by means of glass spacers placed between the PTFE blocks but distanced from the copper plates to avoid surface leakage currents or arcing. The separation distance between the electrodes  
20 can be adjusted, but once chosen, it is fixed for a given set of measurements on a sample. Typically, separations of 0.5 mm to about 2 mm can be used.

The sample is placed on the copper plate serving as the cathode. In the case of a conducting substrate, a sample can be held in place and electrical contact made by applying a small drop of carbon paint to the back of the sample and  
25 allowing it to dry. In the case of an insulating substrate with a conducting film, the substrate is held down on two sides with conducting copper tape, which also serves to provide for electrical contact.

The test apparatus is inserted into a vacuum system, and the system is evacuated to a base pressure below  $1 \times 10^{-6}$  torr ( $1.3 \times 10^{-4}$  Pa). A negative  
30 voltage is applied to the cathode and the emission current is measured as a function of the applied voltage. The separation distance between the plates is measured.

CLAIMS

1. A process for producing a field emission electron emitter, which comprises:

- 5 (a) forming a layer of composite which comprises graphite particles embedded in a matrix material which comprises electrically insulating material, wherein said matrix material adheres to a substrate and to said graphite particles thereby affixing said graphite particles to one another and to said substrate and wherein said graphite particles are essentially completely  
10 surrounded by said matrix material; and  
15 (b) bombarding the surface of the layer formed in (a) with an ion beam which comprises ions of argon, neon, krypton or xenon for a time sufficient to remove said matrix material near the surface of said layer of composite to expose said graphite particles and form whiskers on said graphite particles.

2. The process of claim 1, wherein said ion beam comprises ions of argon.

3. The process of claim 2, wherein said ion beam has a beam energy of from about 0.5 keV to about 2.5 keV.

4. The process of claim 2, wherein said electrically insulating material is  
20 glass.

5. The process of claim 4, wherein said layer of composite is formed by a process, which comprises:

- 25 (a) screen printing a paste comprised of graphite particles and glass frit onto said substrate in the desired pattern; and  
(b) firing the dried patterned paste to soften said glass frit and cause it to adhere to said substrate and to portions of said graphite particles thereby affixing said graphite particles to one another and to said substrate to produce said layer of composite.

6. The process of claim 4, wherein said layer of composite is formed by a  
30 process, which comprises:

- (a) screen printing a paste comprised of graphite particles, glass frit, a photoinitiator and a photohardenable monomer frit onto said substrate in the desired pattern;  
(b) photopatterning the dried paste; and  
35 (c) firing the patterned dried paste to soften said glass frit and cause it to adhere to said substrate and to portions of said graphite particles thereby affixing said graphite particles to one another and to said substrate to produce said layer of composite.

7. An electron emitter made by the process of any of claims 1-6.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/26018

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 H01J9/02 H01J1/30

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 H01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	BAJIC S ET AL: "ENHANCED COLD-CATHODE EMISSION USING COMPOSITE RESIN-CARBON COATINGS" JOURNAL OF PHYSICS D. APPLIED PHYSICS, vol. 21, 1988, pages 200-204, XP002017628 cited in the application see page 202, right-hand column; figures 4,5	1
A	EP 0 700 065 A (AT & T CORP) 6 March 1996 see column 2, line 55 - column 3, line 1 see column 3, line 18 - line 40 --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

18 March 1999

Date of mailing of the international search report

25/03/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,-  
Fax: (+31-70) 340-3016

Authorized officer

Colvin, G

## INTERNATIONAL SEARCH REPORT

International Application No

PCT 98/26018

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 306 246 A (TUCK RICHARD ALLAN ;LATHAM RODNEY VAUGHN (GB); TAYLOR WILLIAM (GB)) 30 April 1997 see page 6, line 1 - line 9 see page 7, line 11 - line 13 see page 9, line 22 - line 24 see page 18, line 9 - line 18 see page 21, line 13 - line 16 ---	1
A	VECHTEN VAN J A ET AL: "KINK SITE SATURATION MECHANISM FOR WHISKER GROWTH UNDER SPUTTERING CONDITIONS" JOURNAL OF CRYSTAL GROWTH, vol. 82, 1987, pages 289-294, XP002057988 cited in the application see abstract ---	1
A	WO 96 00974 A (SILICON VIDEO CORP ;MASSACHUSETTS INST TECHNOLOGY (US); ADVANCED T) 11 January 1996 see page 5, line 30 - page 6, line 1 see page 8, line 8 - line 9 see page 17, line 30 - page 18, line 9 -----	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/26018

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0700065 A	06-03-1996	JP 8077917 A US 5588894 A US 5808401 A US 5698934 A	22-03-1996 31-12-1996 15-09-1998 16-12-1997
GB 2306246 A	30-04-1997	AU 6626096 A CN 1192288 A EP 0842526 A WO 9706549 A GB 2304989 A,B	05-03-1997 02-09-1998 20-05-1998 20-02-1997 26-03-1997
WO 9600974 A	11-01-1996	US 5608283 A AU 7675094 A	04-03-1997 25-01-1996